

InterWrap

32923 Mission Way Mission, B.C. CANADA V2V 6E4

t: 800.567.9727 f: 604.820.5420 w: www.interwrap.com e: info@interwrap.com

PRODUCT SPECIFICATION SHEET

$DURATEX^{TM} EXTRA$

A reinforcing high density polyethylene scrim coated both sides with a uniquely engineered low density polyethylene blend specially designed to provide supperior lumber protection.

PRODUCT SPECIFICATIONS

NOMINAL WEAVE	5 x 4 ppi (20 x 16 tapes per 10 cm)
COATING	Two Sides LDPE @ 0.9 – 1.2 mil thickness, 22.5 - 30 g/m ²
Color	Beige, Black, Clear, White, Yellow
WEIGHT	95 g/m ² ± 5 % (2.8 oz/yd ² ± 5%) finished weight
WIDTHS	Up to 144"

PRODUCT PERFORMANCE

TENSILE STRENGTH ASTM D751-95				
Machine	Force	110 lbs.	50 kg	
Direction	Elongation	25 %		
Cross	Force	65 lbs.	42 kg	
Direction	Elongation	24 %		
TRAPEZOIDAL TEAR STRENGTH ASTM D4533-91				
Machine Direction	Force	64 lbs.	29 kg	
Cross Direction	Force	44 lbs.	20 kg	
UV ACCELERATED WEATHERING ASTM G154-98				
More than 90 % Strength Retained After 2,000 hours* Exposure				
Mullen Bu	MULLEN BURST ASTM D751-95		1104 kPa	
NOMINAL THICKNESS		5.4 mils	0.14 mm	

Note: all values are ± 10%

The test data is based on an average taken over several production runs and should not be considered or interpreted as minimum or maximum values. Values are typical data and not limiting Specifications.

^{*} QUV A-340 lamps 8hrs UV @60°C, 4hrs Condensation @40°C